

TEST REPORT

2026AN2223

DATE OF RECEPTION

Date Format: dd/MM/yyyy 27/08/2026

DATE TESTS

Starting: 27/08/2026

Ending: 18/09/2026

APPLICANT

GABRIEL A/S
HJULMAGERVEJ, 55
DK-9000 Ålborg
Denmark

Att. BENTE ELLINGSOE

IDENTIFICATION AND DESCRIPTION OF SAMPLES

Reference by AITEX	Reference by customer		AITEX sample description
2026AN2223-S01	art.Move	61334 Light Beige	Tejido Fabric
2026AN2223-S02	art.Move	61335 Beige	Tejido Fabric
2026AN2223-S03	art.Move	61336 Beige	Tejido Fabric
2026AN2223-S04	art.Move	61337 Beige	Tejido Fabric
2026AN2223-S05	art.Move	61338 Brown	Tejido Fabric
2026AN2223-S06	art.Move	61339 Dark Brown	Tejido Fabric
2026AN2223-S07	art.Move	62161 Dark Yellow	Tejido Fabric
2026AN2223-S08	art.Move	62162 Dark Yellow	Tejido Fabric
2026AN2223-S09	art.Move	62163 Green Yellow	Tejido Fabric
2026AN2223-S10	art.Move	68335 Yellow Green	Tejido Fabric
2026AN2223-S11	art.Move	61340 Yellow Brown	Tejido Fabric
2026AN2223-S12	art.Move	63157 Brown Orange	Tejido Fabric
2026AN2223-S13	art.Move	61341 Brown	Tejido Fabric
2026AN2223-S14	art.Move	61342 Dark Brown	Tejido Fabric
2026AN2223-S15	art.Move	63158 Light Red Orange	Tejido Fabric
2026AN2223-S16	art.Move	63159 Light Red Orange	Tejido Fabric
2026AN2223-S17	art.Move	63160 Red Orange	Tejido

Tests marked with * are not included within the scope of the ENAC accreditation.





				<i>Fabric</i>
2026AN2223-S18	art.Move	61343	Orange Brown	Tejido <i>Fabric</i>
2026AN2223-S19	art.Move	61344	Orange Brown	Tejido <i>Fabric</i>
2026AN2223-S20	art.Move	64293	Light Red	Tejido <i>Fabric</i>
2026AN2223-S21	art.Move	64294	Red	Tejido <i>Fabric</i>
2026AN2223-S22	art.Move	64295	Dark Red	Tejido <i>Fabric</i>
2026AN2223-S23	art.Move	64296	Dark Red	Fabric
2026AN2223-S24	art.Move	64297	Dark Red	Fabric
2026AN2223-S25	art.Move	66295	Blue	Fabric
2026AN2223-S26	art.Move	66296	Dark Blue	Fabric
2026AN2223-S27	art.Move	66297	Dark Blue	Fabric
2026AN2223-S28	art.Move	66298	Blue	Fabric
2026AN2223-S29	art.Move	66299	Dark Blue	Fabric
2026AN2223-S30	art.Move	67143	Turquoise	Fabric
2026AN2223-S31	art.Move	67144	Dark Turquoise	Fabric
2026AN2223-S32	art.Move	68337	Light Green	Fabric
2026AN2223-S33	art.Move	68338	Green	Fabric
2026AN2223-S34	art.Move	68339	Dark Green	Fabric
2026AN2223-S35	art.Move	68340	Light Green	Fabric
2026AN2223-S36	art.Move	68341	Green	Fabric
2026AN2223-S37	art.Move	68342	Dark Green	Fabric
2026AN2223-S38	art.Move	68343	Dark Green	Fabric
2026AN2223-S39	art.Move	68344	Yellow Green	Fabric
2026AN2223-S40	art.Move	68345	Yellow Green	Fabric
2026AN2223-S41	art.Move	60373	Light Grey	Fabric
2026AN2223-S42	art.Move	60374	Light Grey	Fabric
2026AN2223-S43	art.Move	60375	Grey	Fabric
2026AN2223-S44	art.Move	60376	Dark Grey	Fabric
2026AN2223-S45	art.Move	60377	Dark Brown Grey	Fabric
2026AN2223-S46	art.Move	60999	Black	Fabric

Also covering art.2620

TESTS CARRIED OUT

- COLOUR FASTNESS TO RUBBING.



RESULTS

COLOUR FASTNESS TO RUBBING

Standard

ISO 105-X12:2016

Apparatus

Crockmeter

Starting test date

27/08/2026

Ending test date

17/09/2026

Conditioning time

> 4 H

Atmosphere for conditioning and testing

Temperature	(20±2) °C
Relative Humidity	(65±2) %Hr

Pin

Cylindrical

Applied force

(9 ± 0,2) N

% of water absorption for rubbing in humid

95-100 %

REFERENCE	DIRECTION	DRY STAINING	WET STAINING
2026AN2223-S01	Warp	5	5
	Weft	5	5
2026AN2223-S02	Warp	5	4-5
	Weft	5	4-5
2026AN2223-S03	Warp	5	5
	Weft	5	5
2026AN2223-S04	Warp	5	5
	Weft	5	5
2026AN2223-S05	Warp	4-5	5
	Weft	5	5
2026AN2223-S06	Warp	5	5
	Weft	4-5	5
2026AN2223-S07	Warp	5	5
	Weft	5	5
2026AN2223-S08	Warp	4-5	5
	Weft	5	5
2026AN2223-S09	Warp	5	5
	Weft	5	5
2026AN2223-S10	Warp	5	5



REFERENCE	DIRECTION	DRY STAINING	WET STAINING
2026AN2223-S11	Weft	5	5
	Warp	5	5
2026AN2223-S12	Weft	5	5
	Warp	5	5
2026AN2223-S13	Weft	5	5
	Warp	5	5
2026AN2223-S14	Weft	5	5
	Warp	4-5	5
2026AN2223-S15	Weft	5	5
	Warp	5	5
2026AN2223-S16	Weft	5	5
	Warp	5	5
2026AN2223-S17	Weft	5	5
	Warp	5	5
2026AN2223-S18	Weft	5	5
	Warp	5	5
2026AN2223-S19	Weft	5	5
	Warp	5	5
2026AN2223-S20	Weft	5	5
	Warp	5	5
2026AN2223-S21	Weft	4-5	5
	Warp	4-5	4-5
2026AN2223-S22	Weft	4-5	5
	Warp	4-5	5
2026AN2223-S23	Weft	4-5	5
	Warp	4-5	4-5
2026AN2223-S24	Weft	4-5	4-5
	Warp	5	5
2026AN2223-S25	Weft	5	5
	Warp	4-5	4-5
2026AN2223-S26	Weft	4-5	5
	Warp	5	5
2026AN2223-S27	Weft	5	5
	Warp	4-5	4-5
2026AN2223-S28	Weft	4-5	5
	Warp	5	5
2026AN2223-S29	Warp	5	5



REFERENCE	DIRECTION	DRY STAINING	WET STAINING
2026AN2223-S30	Weft	5	5
	Warp	5	5
2026AN2223-S31	Weft	5	5
	Warp	5	5
2026AN2223-S32	Weft	5	5
	Warp	5	5
2026AN2223-S33	Weft	5	4-5
	Warp	5	4-5
2026AN2223-S34	Weft	5	4-5
	Warp	5	5
2026AN2223-S35	Weft	5	5
	Warp	5	5
2026AN2223-S36	Weft	5	5
	Warp	5	5
2026AN2223-S37	Weft	5	5
	Warp	4-5	4-5
2026AN2223-S38	Weft	4-5	4-5
	Warp	5	5
2026AN2223-S39	Weft	5	5
	Warp	5	5
2026AN2223-S40	Weft	5	5
	Warp	5	5
2026AN2223-S41	Weft	5	5
	Warp	5	5
2026AN2223-S42	Weft	5	5
	Warp	5	5
2026AN2223-S43	Weft	5	5
	Warp	5	5
2026AN2223-S44	Weft	5	5
	Warp	5	4-5
2026AN2223-S45	Weft	5	4-5
	Warp	4	4-5
2026AN2223-S46	Weft	4	4-5

REFERENCE	DIRECTION	DRY CHANGE COLOUR	WET CHANGE COLOUR
2026AN2223-S01	Warp	5	5
	Weft	5	5



REFERENCE	DIRECTION	DRY CHANGE COLOUR	WET CHANGE COLOUR
2026AN2223-S02	Warp	5	5
	Weft	5	5
2026AN2223-S03	Warp	5	5
	Weft	5	5
2026AN2223-S04	Warp	5	5
	Weft	5	5
2026AN2223-S05	Warp	5	5
	Weft	5	5
2026AN2223-S06	Warp	5	5
	Weft	5	5
2026AN2223-S07	Warp	5	5
	Weft	5	5
2026AN2223-S08	Warp	5	5
	Weft	5	5
2026AN2223-S09	Warp	5	5
	Weft	5	5
2026AN2223-S10	Warp	5	5
	Weft	5	5
2026AN2223-S11	Warp	5	5
	Weft	5	5
2026AN2223-S12	Warp	5	5
	Weft	5	5
2026AN2223-S13	Warp	5	5
	Weft	5	5
2026AN2223-S14	Warp	5	5
	Weft	5	5
2026AN2223-S15	Warp	5	5
	Weft	5	5
2026AN2223-S16	Warp	5	5
	Weft	5	5
2026AN2223-S17	Warp	5	5
	Weft	5	5
2026AN2223-S18	Warp	5	5
	Weft	5	5
2026AN2223-S19	Warp	5	5
	Weft	5	5
2026AN2223-S20	Warp	5	5
	Weft	5	5
2026AN2223-S21	Warp	5	5
	Weft	5	5



REFERENCE	DIRECTION	DRY CHANGE COLOUR	WET CHANGE COLOUR
2026AN2223-S22	Warp	5	5
	Weft	5	5
2026AN2223-S23	Warp	5	5
	Weft	5	5
2026AN2223-S24	Warp	5	5
	Weft	5	5
2026AN2223-S25	Warp	5	5
	Weft	5	5
2026AN2223-S26	Warp	5	5
	Weft	5	5
2026AN2223-S27	Warp	5	5
	Weft	5	5
2026AN2223-S28	Warp	5	5
	Weft	5	5
2026AN2223-S29	Warp	5	5
	Weft	5	5
2026AN2223-S30	Warp	5	5
	Weft	5	5
2026AN2223-S31	Warp	5	5
	Weft	5	5
2026AN2223-S32	Warp	5	5
	Weft	5	5
2026AN2223-S33	Warp	5	5
	Weft	5	5
2026AN2223-S34	Warp	5	5
	Weft	5	5
2026AN2223-S35	Warp	5	5
	Weft	5	5
2026AN2223-S36	Warp	5	5
	Weft	5	5
2026AN2223-S37	Warp	5	5
	Weft	5	5
2026AN2223-S38	Warp	5	5
	Weft	5	5
2026AN2223-S39	Warp	5	5
	Weft	5	5
2026AN2223-S40	Warp	5	5
	Weft	5	5
2026AN2223-S41	Warp	5	5
	Weft	5	5



REFERENCE	DIRECTION	DRY CHANGE COLOUR	WET CHANGE COLOUR
2026AN2223-S42	Warp	5	5
	Weft	5	5
2026AN2223-S43	Warp	5	5
	Weft	5	5
2026AN2223-S44	Warp	5	5
	Weft	5	5
2026AN2223-S45	Warp	5	5
	Weft	5	5
2026AN2223-S46	Warp	5	5
	Weft	5	5

///



Reference by AITEX	Description	Reference by customer
2026AN2223-S01	Tejido / Fabric	art.Move 61334 Light Beige
2026AN2223-S02	Tejido / Fabric	art.Move 61335 Beige
2026AN2223-S03	Tejido / Fabric	art.Move 61336 Beige
2026AN2223-S04	Tejido / Fabric	art.Move 61337 Beige
2026AN2223-S05	Tejido / Fabric	art.Move 61338 Brown
2026AN2223-S06	Tejido / Fabric	art.Move 61339 Dark Brown
2026AN2223-S07	Tejido / Fabric	art.Move 62161 Dark Yellow
2026AN2223-S08	Tejido / Fabric	art.Move 62162 Dark Yellow
2026AN2223-S09	Tejido / Fabric	art.Move 62163 Green Yellow
2026AN2223-S10	Tejido / Fabric	art.Move 68335 Yellow Green
2026AN2223-S11	Tejido / Fabric	art.Move 61340 Yellow Brown
2026AN2223-S12	Tejido / Fabric	art.Move 63157 Brown Orange
2026AN2223-S13	Tejido / Fabric	art.Move 61341 Brown
2026AN2223-S14	Tejido / Fabric	art.Move 61342 Dark Brown
2026AN2223-S15	Tejido / Fabric	art.Move 63158 Light Red Orange
2026AN2223-S16	Tejido / Fabric	art.Move 63159 Light Red Orange
2026AN2223-S17	Tejido / Fabric	art.Move 63160 Red Orange
2026AN2223-S18	Tejido / Fabric	art.Move 61343 Orange Brown
2026AN2223-S19	Tejido / Fabric	art.Move 61344 Orange Brown
2026AN2223-S20	Tejido / Fabric	art.Move 64293 Light Red
2026AN2223-S21	Tejido / Fabric	art.Move 64294 Red
2026AN2223-S22	Tejido / Fabric	art.Move 64295 Dark Red
2026AN2223-S23	Fabric	art.Move 64296 Dark Red
2026AN2223-S24	Fabric	art.Move 64297 Dark Red
2026AN2223-S25	Fabric	art.Move 66295 Blue
2026AN2223-S26	Fabric	art.Move 66296 Dark Blue
2026AN2223-S27	Fabric	art.Move 66297 Dark Blue
2026AN2223-S28	Fabric	art.Move 66298 Blue
2026AN2223-S29	Fabric	art.Move 66299 Dark Blue
2026AN2223-S30	Fabric	art.Move 67143 Turquoise
2026AN2223-S31	Fabric	art.Move 67144 Dark Turquoise
2026AN2223-S32	Fabric	art.Move 68337 Light Green
2026AN2223-S33	Fabric	art.Move 68338 Green
2026AN2223-S34	Fabric	art.Move 68339 Dark Green
2026AN2223-S35	Fabric	art.Move 68340 Light Green
2026AN2223-S36	Fabric	art.Move 68341 Green



Reference by AITEX	Description	Reference by customer
2026AN2223-S37	Fabric	art.Move 68342 Dark Green
2026AN2223-S38	Fabric	art.Move 68343 Dark Green
2026AN2223-S39	Fabric	art.Move 68344 Yellow Green
2026AN2223-S40	Fabric	art.Move 68345 Yellow Green
2026AN2223-S41	Fabric	art.Move 60373 Light Grey
2026AN2223-S42	Fabric	art.Move 60374 Light Grey
2026AN2223-S43	Fabric	art.Move 60375 Grey
2026AN2223-S44	Fabric	art.Move 60376 Dark Grey
2026AN2223-S45	Fabric	art.Move 60377 Dark Brown Grey
2026AN2223-S46	Fabric	art.Move 60999 Black



RESULTS

COLOUR FASTNESS TO RUBBING

Standard

AATCC TM 8:2016e (2022)e

Apparatus

Crockmeter

Starting test date

27/08/2026

Ending test date

18/09/2026

Scale used

AATCC Gray scale for staining (AATCC evaluation procedure 2)

Reference	Dry staining	Wet staining
2026AN2223-S01	5	5
2026AN2223-S02	5	5
2026AN2223-S03	4-5	5
2026AN2223-S04	5	5
2026AN2223-S05	5	5
2026AN2223-S06	4-5	5
2026AN2223-S07	5	5
2026AN2223-S08	5	5
2026AN2223-S09	5	5
2026AN2223-S10	5	5
2026AN2223-S11	5	5
2026AN2223-S12	4-5	5
2026AN2223-S13	5	5
2026AN2223-S14	5	5
2026AN2223-S15	5	5
2026AN2223-S16	4-5	5
2026AN2223-S17	5	5
2026AN2223-S18	5	5
2026AN2223-S19	5	5
2026AN2223-S20	5	5
2026AN2223-S21	5	5
2026AN2223-S22	4-5	5
2026AN2223-S23	5	5
2026AN2223-S24	4-5	5
2026AN2223-S25	5	5
2026AN2223-S26	5	5
2026AN2223-S27	5	5
2026AN2223-S28	4-5	5
2026AN2223-S29	4-5	5
2026AN2223-S30	5	5
2026AN2223-S31	4-5	5
2026AN2223-S32	5	5
2026AN2223-S33	5	5
2026AN2223-S34	4-5	5
2026AN2223-S35	5	5
2026AN2223-S36	5	5
2026AN2223-S37	5	5
2026AN2223-S38	4-5	5
2026AN2223-S39	5	5
2026AN2223-S40	5	5
2026AN2223-S41	5	5
2026AN2223-S42	5	5



Reference	Dry staining	Wet staining
2026AN2223-S43	5	5
2026AN2223-S44	5	5
2026AN2223-S45	5	5
2026AN2223-S46	5	5

///



Reference by AITEX	Description	Reference by customer
2026AN2223-S01	Tejido / Fabric	art.Move 61334 Light Beige
2026AN2223-S02	Tejido / Fabric	art.Move 61335 Beige
2026AN2223-S03	Tejido / Fabric	art.Move 61336 Beige
2026AN2223-S04	Tejido / Fabric	art.Move 61337 Beige
2026AN2223-S05	Tejido / Fabric	art.Move 61338 Brown
2026AN2223-S06	Tejido / Fabric	art.Move 61339 Dark Brown
2026AN2223-S07	Tejido / Fabric	art.Move 62161 Dark Yellow
2026AN2223-S08	Tejido / Fabric	art.Move 62162 Dark Yellow
2026AN2223-S09	Tejido / Fabric	art.Move 62163 Green Yellow
2026AN2223-S10	Tejido / Fabric	art.Move 68335 Yellow Green
2026AN2223-S11	Tejido / Fabric	art.Move 61340 Yellow Brown
2026AN2223-S12	Tejido / Fabric	art.Move 63157 Brown Orange
2026AN2223-S13	Tejido / Fabric	art.Move 61341 Brown
2026AN2223-S14	Tejido / Fabric	art.Move 61342 Dark Brown
2026AN2223-S15	Tejido / Fabric	art.Move 63158 Light Red Orange
2026AN2223-S16	Tejido / Fabric	art.Move 63159 Light Red Orange
2026AN2223-S17	Tejido / Fabric	art.Move 63160 Red Orange
2026AN2223-S18	Tejido / Fabric	art.Move 61343 Orange Brown
2026AN2223-S19	Tejido / Fabric	art.Move 61344 Orange Brown
2026AN2223-S20	Tejido / Fabric	art.Move 64293 Light Red
2026AN2223-S21	Tejido / Fabric	art.Move 64294 Red
2026AN2223-S22	Tejido / Fabric	art.Move 64295 Dark Red
2026AN2223-S23	Fabric	art.Move 64296 Dark Red
2026AN2223-S24	Fabric	art.Move 64297 Dark Red
2026AN2223-S25	Fabric	art.Move 66295 Blue
2026AN2223-S26	Fabric	art.Move 66296 Dark Blue
2026AN2223-S27	Fabric	art.Move 66297 Dark Blue
2026AN2223-S28	Fabric	art.Move 66298 Blue
2026AN2223-S29	Fabric	art.Move 66299 Dark Blue
2026AN2223-S30	Fabric	art.Move 67143 Turquoise
2026AN2223-S31	Fabric	art.Move 67144 Dark Turquoise
2026AN2223-S32	Fabric	art.Move 68337 Light Green
2026AN2223-S33	Fabric	art.Move 68338 Green
2026AN2223-S34	Fabric	art.Move 68339 Dark Green
2026AN2223-S35	Fabric	art.Move 68340 Light Green
2026AN2223-S36	Fabric	art.Move 68341 Green



Reference by AITEX	Description	Reference by customer
2026AN2223-S37	Fabric	art.Move 68342 Dark Green
2026AN2223-S38	Fabric	art.Move 68343 Dark Green
2026AN2223-S39	Fabric	art.Move 68344 Yellow Green
2026AN2223-S40	Fabric	art.Move 68345 Yellow Green
2026AN2223-S41	Fabric	art.Move 60373 Light Grey
2026AN2223-S42	Fabric	art.Move 60374 Light Grey
2026AN2223-S43	Fabric	art.Move 60375 Grey
2026AN2223-S44	Fabric	art.Move 60376 Dark Grey
2026AN2223-S45	Fabric	art.Move 60377 Dark Brown Grey
2026AN2223-S46	Fabric	art.Move 60999 Black

**MEANING OF COLOUR FASTNESS APPRAISAL EVALUATED WITH GREY SCALE**

VALUE	MEANING
5	VERY GOOD - EXCELLENT
4	GOOD
3	FAIR - MODERATE
2	POOR - BEHAVIOUR
1	VERY POOR

According to standards ISO 105-A02 e ISO 105-A03



Isabel Soriano
Laboratories and International Offices Subdirector



Date: 25/09/2026 11:38:55

Digitally Signed by: MARIA ISABEL SORIANO SARRIO -

NIF: 52716426N

LIABILITY CLAUSES

- 1.- AITEX is liable only for the results of the methods of analysis used, as expressed in the report and referring exclusively to the materials or samples indicated in the same which are in its possession, the professional and legal liability of the Centre being limited to these. Unless otherwise stated, the samples were freely chosen and sent by the applicant.
- 2.- AITEX shall not be liable in any case of misuse of the test materials nor for undue interpretation or use of this document. AITEX laboratories do not carry out sampling.
- 3.- The Offer and / or Order to which the applicant gives approval through signature and seal, constitutes the Legally Executable Agreement in which AITEX is responsible for safeguarding and guaranteeing the absolute confidentiality of the management of all the information obtained or created during the performance of the contracted activities.
- 4.- In the eventuality of discrepancies between reports, a check to settle the same will be carried out in the head offices of AITEX. Also, the applicants undertake to notify AITEX of any complaint received by them as a result of the report, exempting this Centre from all liability if such is not done, the periods of conservation of the samples being taken into account.
- 5.- AITEX will provide at the request of the person concerned, the treatment of complaints procedure. In the event that you want to make it, direct it to: calidad@aitex.es.
- 6.- AITEX is not responsible for the information provided by customers, which is reflected in the Report, and may affect the validity of the results.
- 7.- AITEX is not responsible for an inadequate state of the sample received that could compromise the validity of the results, expressing such circumstance, in the test reports.
- 8.- AITEX may include in its reports, analyses, results, etc., any other evaluation which it considers necessary, even when it has not been specifically requested.
- 9.- When a Declaration of Conformity is requested, if not indicated otherwise, the decision rule according to ILAC-G8: 2009 will be applied with a security zone of 1U and a Probability of False Acceptance <2.5%.
- 10.- The uncertainties of tests, which are made explicit in the Results Report, have been estimated for a $k = 2$ (95% probability of coverage). If not informed, they are available to the client in AITEX.
- 11.- The original materials and rests of samples, not subject to test, will be retained in AITEX during the twelve months following the issuance of the report, so that any check or claim which, in his case, wanted to make the applicant, should be exercised within the period indicated.
- 12.- This report may only be sent or delivered by hand to the applicant or to a person duly authorised by the same.
- 13.- The results of the tests and the statement of compliance with the specification in this report refer only to the test sample as it has been analyzed / tested and not the sample / item which has taken the test sample.
- 14.- The client must attend at all times, to the dates of the realization of the tests.
- 15.- According to Resolution EA (33) 31, the test reports must include the unique identification of the sample, and any brand or label of the manufacturer may be added. It is not allowed to re-issue test reports of untested sample names (references), they can only be re-issued for error correction or inclusion of omitted data that were already available at the time of the test. The laboratory can not assume responsibility for declaring that the product with the new trade name / trademark is strictly identical to the one originally tested; This responsibility belongs to the client.
- 16.- This report may not be partially reproduced without the written approval of the issuing laboratory.