



Test
TS EN ISO/IEC 17025
AB-0342-T

AB-0342-T

144444140a

09/26

TÜV Rheinland
Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş.
Saniye Ermutlu Sokak Çolakoğlu Plaza B Blok No :12 Kozyatağı-İSTANBUL

Page 1 of 4

Test Report

GABRIEL A/S

Hjølmgærvej, Aalborg DK-9000, Denmark

Report No. 144444140a
Buyer /
Test Item. : Europost col.66039
Lot No. : /
Manufacturer : /
Fiber Content. : /
Colour Name. : /
Article No. : /
End Use. : /
Test Scope. : Customer selected parameters.
Remark : Revised of test report 144444140 dated 09.09.2026, Pilling Resistance test result has been removed, upon client's request. The preceding report is no longer valid.

Applicant's Provided Care Instruction/Label:

Sample Receiving date: 2026-08-26 p.m.
Testing Period: 2026-08-27 to 2026-09-09
Report Date: 2026-09-29
Test Result: Pass

TÜV Rheinland Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş. accredited by TÜRKAK under registration number AB-0342-T for ISO/IEC 17025-2017 as test laboratory

The Turkish Accreditation Agency (TÜRKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of the test reports.

The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following, pages which are part of this report

For and on behalf of
TÜV Rheinland Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş.

Elif Kocasalli / CR Assistant
Project Manager

Abdullah Akil / Physical
Laboratory Manager

TÜV Rheinland Uluslararası Standartlar Sertifikasyon ve Denetim A.Ş.

Kozyatagi Mah. Saniye Ermutlu Sok. No:12
Colakoglu Plaza B Blok 34742 Kadikoy Istanbul,
Tel. +902166653200, Fax +902166653299, e-mail: info@tr.tuv.com

The results given in this report belong to the received sample by vendor.

This test report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid.

This test report is signed by digital signature.

TÜV Rheinland testing laboratories apply the Zero Guard band rule for statement of conformity evaluation, unless other decision rule is required by the customer.

AB-0342-T
144444140a
09/26

Test Result Summary :

Test Specification:

1 Abrasion Resistance - Determination Of Specimen Breakdown

Test result:

PASS

AB-0342-T
144444140a
09/26

1. Photo



2. List of Materials

Material List:

Material No.	Material	Color	Location
M001	Textile	Blue	Woven base (Europost col.66039)

AB-0342-T
144444140a
09/26

1.Abrasion Resistance - Determination Of Specimen Breakdown

Test method : Abrasion Resistance - Determination Of Specimen Breakdown (EN ISO 12947-2: 2016 / AC: 2006 acc. to EN ISO 14465: 12kPa Martindale)

Load : 12kPa
50.000 rubs / Change after 3000 rubs

	<u>M001</u>	<u>Requirement</u>
Shade Change 3000 rubs	4-5	-
Abrasion revs	>50.000 cycles	50000

Remark : No threads broken

- END -